



**Test Report**

No. [REDACTED]

Date: SEP 04, 2007

Page 1 of 3

[REDACTED] HONG KONG

The following sample(s) was/were submitted and identified on behalf of the applicant as [REDACTED] LAMINATING FILM

SGS Ref No. : [REDACTED]  
Sample Receiving Date : AUG 30, 2007  
Testing Period : AUG 30, 2007 TO SEP 04, 2007

TEST REQUESTED : As specified by client, to test soluble Lead, soluble Antimony, soluble Arsenic, Soluble Barium, soluble Cadmium, soluble Chromium, soluble Mercury, soluble Selenium content in the submitted sample.

TEST METHOD : With reference to EN71 part 3 : 1994 (including amendment A1:2000/ AC:2002). Analysis was performed by Atomic Absorption Spectrometer & Inductively Coupled Plasma Atomic Emission Spectrometer (ICP-AES).

RESULTS : Please refer to next page.

Signed for and on behalf of  
SGS-CSTC Ltd.

Jiang YongPing, Terry  
Sr Engineer



**Test Report**

No. [REDACTED]

Date: SEP 04, 2007

Page 2 of 3

Results :

EN71 Part 3 : 1994 (including amendment A1:2000/ AC:2002) - Migration of Certain Elements

<u>Element</u>	<u>No.1</u>	<u>Limit</u>
Soluble Lead ( Pb )	< 5	90 mg/kg
Soluble Antimony ( Sb )	< 2	60 mg/kg
Soluble Arsenic ( As )	< 2	25 mg/kg
Soluble Barium ( Ba )	29	1000 mg/kg
Soluble Cadmium ( Cd )	< 5	75 mg/kg
Soluble Chromium ( Cr )	< 5	60 mg/kg
Soluble Mercury ( Hg )	< 2	60 mg/kg
Soluble Selenium ( Se )	< 5	500 mg/kg

Note : - < = Less than  
- The unit of results is mg per kg

Test Part Description:

No.1 Transparent sheet




**Test Report**

No. [REDACTED]

Date: SEP 04, 2007

Page 3 of 3

Sample photo :



SGS authenticate the photo on original report only

\*\*\* End of Report \*\*\*